

# **TEST REPORT**

## Laboratory test on a Synthetic Turf

Tests performed according to ASTM D5034



This report contains 2 pages in total. Reproduction of this report is authorized only in its entire form. Results reported are valid only for the products tested. To declare the conformity (or not), the uncertainty of the results was not taken into account. Detailed results are available on request.

LABOSPORT, THE WORLD LEADING SPORTS SURFACES EXPERT

**LABOSPORT USA Inc** • 1806 S Dixie Highway suite G • Dalton • Georgia • 30720 Email: contact@labosport.com • Telephone: (706) 529–9474

www.labosport.com





#### **INFORMATION**

Product description	Synthetic turf				
Product name	Vista Natural 65				
Sample number	U\$00581				
Date of Reception	March 29 <sup>th</sup> , 2021				
Date of Testing	March 30 <sup>th</sup> , 2021				
Temperature	Min	70°F	Max	73°F	
Humidity	Min	49 %	Max	51 %	

#### **PHOTOS OF THE SAMPLES**



US00581 – Vista Natural 65 Turf face view

## RESULTS



US00581 – Vista Natural 65 Turf backing view

Property	Method	Condition	Unit	Direction	Results (average)
Grab Test AST		Dry	Lbf	Warp	550
	ASTM D5034			Weft	507

### **REPORTED BY**

Loïc Schuffenecker (Laboratory Technician) - Writer

Thomas Amadei, T.P. (Laboratory Manager) - Approver