


TEST REPORT

Laboratory test on a Synthetic Turf

Tests performed according to ASTM D5034



This report contains 2 pages in total. Reproduction of this report is authorized only in its entire form. Results reported are valid only for the products tested. To declare the conformity (or not), the uncertainty of the results was not taken into account. Detailed results are available on request.

LABOSPORT, THE WORLD LEADING SPORTS SURFACES EXPERT

LABOSPORT USA Inc • 1806 S Dixie Highway suite G • Dalton • Georgia • 30720 Email: contact@labosport.com • Telephone: (706) 529–9474

www.labosport.com





INFORMATION

Product description	Synthetic turf				
Product name	Vista Sport				
Sample number	US00589				
Date of Reception	March 29 th , 2021				
Date of Testing	March 30 th , 2021				
Temperature	Min	70°F	Max	73°F	
Humidity	Min	49 %	Max	51 %	

PHOTOS OF THE SAMPLES



US00589 – Vista Sport Turf face view

RESULTS



US00589 – Vista Sport Turf backing view

Property	Method	Condition	Unit	Direction	Results (average)
Grab Test ASTM D5034		Dry	Lbf	Warp	563
	A311VI D5034			Weft	463

REPORTED BY

Loïc Schuffenecker (Laboratory Technician) - Writer

Thomas Amadei, T.P. (Laboratory Manager) - Approver

Report number:	R21038US-L1
Date:	April 1 st , 2021